

hour).

Claim 3 (amended). Masking strip according to Claim 1, [characterized in that] wherein the adhesive tape (1) is 15-75 mm wide[, especially 19-30 mm wide].

9
Claim 4 (amended). Masking strip according to Claim 1, [characterized in that] wherein the paper support (2) is creped, stretchable and flexible and has good paint adhesion, and the entire adhesive tape (1) has a thickness of 100-250 μm [, especially 130-200 μm].

Claim 5 (amended). Masking strip according to Claim 1, [characterized in that] wherein the masking paper (5) is an unbleached kraft paper of 30-40 g/m^2 and a width of [especially] 15-50 cm[, very especially 20-40 cm].

Claim 6 (amended). Masking strip according to Claim 1, [characterized in that] wherein the masking film (6) is a polyolefin film 7-40[, especially 8-20] μm thick, [especially of polyolefin, especially polyethylene, and especially] which is corona pretreated, [whose width amounts especially to] and is 0.5-2 m wide.

Claim 7 (amended). Masking strip according to Claim 1, [characterized in that] wherein the masking film (6) is folded [extensibly, especially] according to the dimensions of the masking paper (5) and is folded against the latter accordion-wise.

1a

~~SECRET~~

to

20092

-- 11. A method for painting an automobile, wherein parts of the automobile are not to be painted, which comprises masking parts of said automobile which are not to be painted with a masking strip according to Claim 1. --

REMARKS
